

Outer Shell Fabric and Finish	Condition	Direction	Indices of Penetration, Repellency, Absorption			Flame Resistance	
			$I_P$	$I_R$	$I_A$	Average Afterflame (s)	Average Char Length (mm)
Agility <i>Durable Water Repellent Finish</i>	Fuel Contamination	Warp	26.6	1.3	67.9	17.5	0
		Fill	19.4	0.1	65.7	27.8	0
	Fuel Contamination followed by Cleaning	Warp	35.0	0.5	68.2	0.2	0
		Fill	30.7	1.1	70.8	1.2	0
	As Received	Warp	N/A	N/A	N/A	0.0	5
		Fill	N/A	N/A	N/A	0.0	4
	After 5 Launderings	Warp	N/A	N/A	N/A	0.0	4
		Fill	N/A	N/A	N/A	0.0	4