

Outer Shell Fabric and Finish	Condition	Direction	Indices of Penetration, Repellency, Absorption			Flame Resistance	
			$I_P$	$I_R$	$I_A$	Average Afterflame (s)	Average Char Length (mm)
Armor AP	Fuel Contamination	Warp	32.9	0.0	66.2	15.7	5
		Fill	34.0	0.0	66.6	16.4	5
	Fuel Contamination followed by Cleaning	Warp	28.1	1.3	68.5	1.1	13
		Fill	31.0	0.0	68.8	1.9	14
	As Received	Warp	N/A	N/A	N/A	0.0	14
		Fill	N/A	N/A	N/A	0.0	15
	After 5 Launderings	Warp	N/A	N/A	N/A	0.0	12
		Fill	N/A	N/A	N/A	0.0	14