

Outer Shell Fabric and Finish	Condition	Direction	Indices of Penetration, Repellency, Absorption			Flame Resistance	
			I_P	I_R	I_A	Average Afterflame (s)	Average Char Length (mm)
Brigade 750 <i>Durable Water Repellent Finish</i>	Fuel Contamination	Warp	29.0	1.1	73.2	29.9	128
		Fill	28.6	0.2	81.9	21.7	67
	Fuel Contamination followed by Cleaning	Warp	28.6	-4.1	72.5	17.4	48
		Fill	29.6	-4.0	69.9	8.7	47
	As Received	Warp	N/A	N/A	N/A	0.0	68
		Fill	N/A	N/A	N/A	0.0	81
	After 5 Launderings	Warp	N/A	N/A	N/A	0.3	59
		Fill	N/A	N/A	N/A	0.6	60