

Outer Shell Fabric and Finish	Condition	Direction	Indices of Penetration, Repellency, Absorption			Flame Resistance	
			I_P	I_R	I_A	Average Afterflame (s)	Average Char Length (mm)
Flex7 <i>Durable Water Repellent Finish</i>	Fuel Contamination	Warp	27.6	1.5	67.7	26.5	2
		Fill	31.2	0.5	65.2	25.3	2
	Fuel Contamination followed by Cleaning	Warp	32.4	0.5	65.7	0.0	0
		Fill	27.1	0.6	68.5	0.0	7
	As Received	Warp	N/A	N/A	N/A	0.0	13
		Fill	N/A	N/A	N/A	0.0	14
	After 5 Launderings	Warp	N/A	N/A	N/A	0.0	12
		Fill	N/A	N/A	N/A	0.0	12