

Outer Shell Fabric and Finish	Condition	Direction	Indices of Penetration, Repellency, Absorption			Flame Resistance	
			I_P	I_R	I_A	Average Afterflame (s)	Average Char Length (mm)
Gladiator 750 <i>Durable Water Repellent Finish</i>	Fuel Contamination	Warp	25.3	0.5	72.0	33.4	97
		Fill	28.2	0.4	71.8	23.0	108
	Fuel Contamination followed by Cleaning	Warp	27.4	0.4	70.4	8.9	49
		Fill	27.0	0.1	70.7	7.7	46
	As Received	Warp	N/A	N/A	N/A	0.0	80
		Fill	N/A	N/A	N/A	0.1	85
	After 5 Launderings	Warp	N/A	N/A	N/A	0.4	61
		Fill	N/A	N/A	N/A	0.4	60