

Outer Shell Fabric and Finish	Condition	Direction	Indices of Penetration, Repellency, Absorption			Flame Resistance	
			I_P	I_R	I_A	Average Afterflame (s)	Average Char Length (mm)
MPG S000107505 Horizon Gold - Hydropel Finish (non-PFAS water repel)- 7.0 osy	Fuel Contamination	Warp	28.1	0.0	70.1	22.1	22
		Fill	28.0	0.0	71.2	32.3	19
	Fuel Contamination followed by Cleaning	Warp	24.7	0.0	68.8	3.8	32
		Fill	23.3	0.0	75.2	2.2	32
	As Received	Warp	N/A	N/A	N/A	0.0	38
		Fill	N/A	N/A	N/A	0.0	40
	After 5 Launderings	Warp	N/A	N/A	N/A	0.1	34
		Fill	N/A	N/A	N/A	0.0	32