

Outer Shell Fabric and Finish	Condition	Direction	Indices of Penetration, Repellency, Absorption			Flame Resistance	
			I_P	I_R	I_A	Average Afterflame (s)	Average Char Length (mm)
PBI MAX 7.0	Fuel Contamination	Warp	30.7	4.6	61.7	25.8	14
		Fill	30.7	6.0	62.3	20.1	12
	Fuel Contamination followed by Cleaning	Warp	23.8	10.3	63.5	0.0	13
		Fill	23.6	12.6	60.2	0.0	19
	As Received	Warp	N/A	N/A	N/A	0.0	18
		Fill	N/A	N/A	N/A	0.0	19
	After 5 Launderings	Warp	N/A	N/A	N/A	0.0	18
		Fill	N/A	N/A	N/A	0.0	18