

Outer Shell Fabric and Finish	Condition	Direction	Indices of Penetration, Repellency, Absorption			Flame Resistance	
			I <sub>P</sub>	I <sub>R</sub>	I <sub>A</sub>	Average Afterflame (s)	Average Char Length (mm)
<b>MPG</b> <b>S000106175</b> Westex® Synergy - Hydropel Finish (non-PFAS water repel) - 7.5 oz/y	Fuel Contamination	Warp	31.2	13.7	100.0	41.5	85
		Fill	31.2	12.1	97.6	36.2	222
	Fuel Contamination followed by Cleaning	Warp	19.4	0.2	76.4	16.9	103
		Fill	20.0	0.3	82.5	12.0	104
	As Received	Warp	N/A	N/A	N/A	0.0	82
		Fill	N/A	N/A	N/A	0.0	82
	After 5 Launderings	Warp	N/A	N/A	N/A	0.7	70
		Fill	N/A	N/A	N/A	0.4	65